

OVERVIEW TECHNICAL DATA

FRATHERNIT® DN

Product description	Engineered composite material made of resin-bound glass fiber and fillers
Standard colour	white
Main applications	Pressure resistant insulation material for tool- and mouldindustry
Delivery program	Sheets, panels and highly precise machined parts and finished components

Physical characteristics

Properties	Test Standard	Unit	Typical value
Specific density	ISO 1183	g/cm ³	1,8
Water absorption	ISO 62	%	0,3

Thermal characteristics

Properties	Test Standard	Unit	Typical value
Operating temperature, continuous	—	°C	200
Operation temperature, short-term	—	°C	210
Coeff. of linear thermal expansion	DIN 51045	10 ⁻⁶ x K ⁻¹	18
Thermal conductivity	—	W/mK	0,18

Mechanical characteristics

Properties	Test Standard	Unit	Typical value
Compressive strength at 23 °C	ISO 604	N/mm ²	330
Compressive strength at 200 °C	ISO 604	N/mm ²	120
Flexural strength at 23 °C	ISO 178	N/mm ²	140

Issue: 11/2014

We reserve the right to make changes in the context of further technical developments. The guide values listed in this data sheet are not contractual data.

Please contact our applications and sales engineers to clarify the suitability of the material for your application.