

## PressTherm® WD 20

Product description	scription Engineered composite material made of resin-bound glass fabric	
Standard colour	ard colour yellow-brown	
Main applications	ications Thermal insulation parts for heated presses	
Delivery program	Sheets, panels and highly precise machined parts and finished components	

## **Physical characteristics**

Properties	Test Standard	Unit	Typical value
Specific gravity	ISO 1183	g/cm³	1,9
Water absorption	ISO 62	%	0,1

## Thermal characteristics

Properties	Test Standard	Unit	Typical value
Operating temperature, continuous	_	°C	200
Operating temperature, short-term	_	°C	210
Coeff. of linear thermal expansion	DIN 51045	10 <sup>-6</sup> x K <sup>-1</sup>	20
Thermal conductivity	DIN 52612	W/mK	0,21

## **Mechanical characteristics**

Properties	Test Standard	Unit	Typical value
Compressive strength at 23 °C	ISO 604	N/mm <sup>2</sup>	500
Compressive strength at 200 °C	ISO 604	N/mm <sup>2</sup>	260
Flexural strength at 23 °C	ISO 178	N/mm <sup>2</sup>	500
Modul of elasticity at 23 °C	ISO 178	N/mm <sup>2</sup>	21000
Rate of Settling at 200 °C and 30 N/mm <sup>2</sup>	_	%	1,0
Split load	DIN 53463	N	3500

Issue: 11/2014

We reserve the right to make changes in the context of further technical developments. The guide values listed in this data sheet are not contractual data.

Please contact our applications and sales engineers to clarify the suitability of the material for your application.